

TECHNICAL DATA SHEET

PROMINENT PREMIUM EGGSHELL ENAMEL

Date: January 2021



THIS SUPERCEDES ALL PREVIOUS PUBLICATIONS

PRODUCT DESCRIPTION

Premium quality alkyd based eggshell enamel.

INTENDED USES:

1. Final coat for only interior correctly primed cement plaster, wood, hardboard or metal.
2. Ideal for bathrooms and kitchens walls and ceilings.

FEATURES:

1. Appearance Sheen.
2. Scrubbable Ideal for kitchens, bathrooms and passages where cleaning is done often.
3. Good hiding ability.
4. Resistant to normal kitchen fumes.
5. Can be tinted to specific colour requirements.

PRODUCT INFORMATION:

Appearance:	Sheen.
Colours:	White and tint bases to tint most of the colours on the tint system.
Solids:	79.3% by mass and 63.9% by volume.
Density:	1,45kg/l.
Recommended Wet Film Thickness:	63µm
Recommended Dry Film Thickness:	2 coats x 40µm per coat minimum.
Spreading rate:	8 - 10m ² /l dependent on surface texture and porosity.
Viscosity at 23°C:	85-95Kµ.
Flash point:	45°C
Respecting the environment:	Dispose of excess product and containers in a responsible manner without harming the environment.

This product is manufactured under strict SABS ISO 9001:2015 quality standards

STORAGE:

Keep containers properly sealed.
Store away from direct heat, sun and severe cold in a place with adequate ventilation.

PACKAGING:

White and Clear Tinting Base
1Lt, 5Lt & 20Lt

TECHNICAL DATA SHEET

PROMINENT PREMIUM EGGSHELL ENAMEL

APPLICATION DETAILS:

Mixing:	Stir well before use with a flat paddle to an even consistency. Stir occasionally during use.		
Method:	Roller (use short nap roller - mohair), brush or airless spray gun.		
Thinning:	Not recommended. Use Mineral Turpentine if required.		
Cleaning:	Remove as much of the product as possible from the application equipment before cleaning with Prominent Mineral Turpentine.		
Application Conditions:	<u>Surface Temperature</u>	<u>Ambient Temperature</u>	<u>Relative Humidity</u>
	Min: 5°C	Min: 5°C	Min: 10°C
	Or 3°C above dew point, if possible away from direct sunlight.		
	Max: 40°C	Max: 40°C	Max: 85°C
Drying time:	<u>Touch dry:</u> 4h at 23°C	<u>Recoating time:</u> 16h at 23°C	
	Note: higher temperatures will accelerate the drying times (approximately halved for every 10°C increase) whilst lower temperatures will retard the drying times (approximately doubled for every 10°C decrease).		
Requirements:	2 coats minimum. Some bright and chromatic colours may require additional coats.		

SURFACE PREPARATION

Surfaces must be sound, clean and dry (moisture content below 15%) before painting. Newly applied plaster need to be left for 21 to 28 days or 1 week for every 5mm thickness of plaster. Undesirable weather conditions e.g. cold or wet weather conditions will results in extended curing period.

Plaster sand to comply with SABS 1090 requirements. Plaster mix must have a minimum thickness of 10mm, free from soft and friable material and comply with SABS 0164-1 for strength (MPA).

1. New work:

- | | |
|-----------------------------|---|
| 1.1 Interior cement plaster | 1 coat Prominent Select Plaster Primer or Dampcure. |
| 1.2 Gypsum plaster | 1 coat Prominent Select Plaster Primer or Dampcure. |
| 1.3 Metal (new) | Degrease with Prominent General Purpose Cleaner at a diluted ratio of 1:10 with water and abrasive pads. Rinse with clean water. Allow to dry. Apply 2 coats Prominent Rust Primer and 1 coat Prominent Select Universal Undercoat. |
| 1.4 Metal (rusted) | Degrease with Prominent General Purpose Cleaner at a diluted ratio of 1:10 with water and abrasive pads. Remove surface rust using Multi Surface Etch Cleaner and allow reaction for 20 minutes using a scouring pad. Rinse with clean water. Allow to dry and apply 2 coats Prominent Rust Primer and 1 coat Prominent Select Universal Undercoat. |
| 1.5 Wood | 1 coat Prominent Wood Primer. |

2. Redecorating:

- | | |
|--------------------------------|--|
| 2.1 Gloss enamel | Sand down, remove dust and apply directly. |
| 2.2 Sound matt emulsion paint | Clean well and apply directly. |
| 2.3 Sound sheen emulsion paint | Sand down and apply directly. |
| 2.4 Poor condition surfaces | Strip down and treat as new work. |

TECHNICAL DATA SHEET

PROMINENT PREMIUM EGGSHELL ENAMEL

LIMITATIONS:

1. Cannot be applied to unprimed surfaces.
2. Can only be applied under specified conditions.
3. Cannot be applied over poor quality undercoats or directly onto gypsum plaster.
4. Application must be even to prevent variations in gloss levels.
5. Spot touch-ups will lead to variation in gloss levels and colour.
6. Very cold conditions will lengthen drying time.
7. Moisture content must not exceed 15% and for interior applications.
8. Yellowing tends to occur in dark areas.
9. To ensure a consistent colour appearance, ensure that batch numbers on all the containers are the same. Where the batch numbers differ, intermix before use.
10. When tinting dark colours from a clear tint base, note that the recommended DFT could be lower due to the volume solid content. For this reason additional coats may be required to achieve good opacity and an aesthetically pleasing finish.

SAFETY PRECAUTIONS:

1. Keep out of reach of children.
2. Ensure to maintain good ventilation during application and drying process.
3. Wear a suitable dust mask if sanding.
4. In case of skin contact, wash with soap and water or a recognised skin cleaner. Avoid contact with eyes. In case of contact with eyes rinse immediately with running water and seek medical advice.
5. If product is ingested drink plenty of water. Do not induce vomiting at any time. Seek medical advice.
6. Do not smoke while painting.
7. Refer to the Material Safety Data Sheet (MSDS) for detailed information about the product and transportation and classification criteria. MSDS is available on www.prominentpaints.co.za or from Prominent Customer Service Department.
8. To avoid any risk of spillage, always transport in a secure upright position.

TINT BASE:

Characteristics:

1. The tint base containers are only filled to levels which are specific for each tint base to allow the calculated volume of colourant to be added in order to achieve the volume indicated on the container after tinting.
2. Tint bases and colourants are unfinished products which should not be used on their own.
3. Only once the prescribed colourant is added to the specific tint base will the finished product comply with the technical features and related information as set out in this TDS.

Product Information:

1. Colourant to be used: Prominent colourants are specifically formulated for use with Prominent Pro-Matic tinting system. ICC colourants which are using only Prominent Paints supported formulations on Largo 2000.
2. Tint Bases: White and Clear Tint Base.

TECHNICAL DATA SHEET

PROMINENT PREMIUM EGGSHELL ENAMEL

DISCLAIMER:

The information contained herein is given in good faith and is meant merely as a guide for the specifier or user. It is gained from results obtained from our experience and tests carried out under controlled conditions. No warranty/guarantee is implied since the conditions of use, application method, substrate and cleanliness of the substrate are beyond Prominent Paints control. For a surface specific specification contact Prominent Paints Customer Service Department for assistance. This issue supersedes all previous publications.

Important Note; Technology may change with time, necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used for reference. Prominent Paints Technical Data Sheets are available on www.prominentpaints.co.za or from Prominent Paints Customer Service Department.

Prominent (Pty) Ltd.
11 Dan Jacobs Street.
Alrode Alberton 1449
P.O. Box 136166
Alberton North 1456

Customer Service Department:
Tel: +27 86 177 6646
Tel: +27 11 389 4746

Reg. No. 1997/006763/07